





ISO 6530

| | |
|--------------------|------------------------------------|
| Method Number | Tested in Accordance with ISO 6530 |
| Log Number | 03044-9-01 |
| Job Number | J044T06 |
| Test Date | 6/5/03 |
| Test Temp | 20 degrees Celsius |
| Material Identity | Labcoat Material BodyGardz |
| Chemical | Diethylamine |
| CAS Number | 109-89-7 |
| Density g/mL | 0.99 |
| Mass per Unit Area | 147.14 gm per meter squared |


 ANALYST
 Chris Moreland


 QC
 Jeff Krueger

| Warp Sample | Index of Penetration | Index of Repellency | Flow Rate Low |
|-------------|----------------------|---------------------|-----------------|
| 1 | 24.85% | 28.89% | 10 ml in 10 sec |
| 2 | 24.24% | 28.79% | 10 ml in 10 sec |
| 3 | 25.25% | 29.29% | 10 ml in 10 sec |
| Fill Sample | | | |
| 1 | 28.79% | 25.35% | 10 ml in 10 sec |
| 2 | 29.29% | 24.95% | 10 ml in 10 sec |
| 3 | 29.19% | 24.85% | 10 ml in 10 sec |

The testing herein is based upon accepted industry practice as well as the test method listed. Test results reported herein do not apply to samples other than those tested. TRI/Austin, Inc. neither accepts responsibility for nor makes claim as to the final use and purpose of the material. TRI/Austin, Inc. observes and maintains client confidentiality, and limits reproduction of this report, except in full, without prior approval of TRI/Austin, Inc.

10R-110 Rev0